



Lube Control Pty Ltd



Product Data

Perfecto XEP Range

Premium antiwear turbine lubricant

Description

The Castrol Perfecto XEP range of turbine oils is formulated from severely hydro treated premium mineral base stocks together with a complex additive system to provide requisite anti wear performance and oxidative stability.

Application

The Perfecto XEP range is primarily intended for the lubrication of highly loaded industrial gas turbines, aero derivative power turbines & driven machinery and turbo machinery where the lubricant is exposed to high local temperatures during operation and the heat soaking period during run down.

The Perfecto XEP range possess the requisite air release, foaming and water separation properties for steam turbines making them suitable and compliant for gas and steam turbines in single train sharing a common oil reservoir.

Specific grades within the Perfecto XEP range meet or exceed the requirements of:

- BS 489: 1999
- DIN 51515 Part 1 (L-TD)
- DIN 51515 Part 2 (L-TG)
- General Electric
 - GEK 28143b
 - GEK 32568k
 - GEK 46506E
 - GEK 101941A
 - GEK 107395A
- General Electric Oil & Gas
 - ITN 52220.02
 - ITN 52220.03
- Alstom HTGD 90117
- Siemens
 - TLV 9013 04
 - TLV 9013 05
 - MAT812108
 - MAT812109
- Solar ES 9-224 AA Class II

Product Performance Claims

- Meets or exceeds a wide range of both steam and gas turbine specifications
- Designed for a wide range of applications making it possible to rationalise grades without risk of misapplication
- Excellent thermal / oxidation stability
- Good water separation and corrosion inhibition performance

Typical Characteristics

Name	Method	Units	Perfecto XEP 32	Perfecto XEP 46
ISO Viscosity Grade	-	-	32	46
Density @ 15°C / 59°F	ISO 12185 / ASTM D4052	kg/m³	859	863
Kinematic Viscosity @ 40°C / 104°F	ISO 3104 / ASTM D445	mm²/s	32	46
Kinematic Viscosity @ 100°C / 212°F	ISO 3104 / ASTM D445	mm²/s	5.5	7.0
Viscosity Index	ISO 2909 / ASTM D2270	-	111	108
Foam Sequence I - tendency / stability	ISO 6247 / ASTM D892	ml/ml	10/0	10/0
Air Release @ 50°C / 122°F	ISO 9120 / ASTM D3427	minutes	2	2
Demulsification - Steam method	IP 19	seconds	75	95
Water Separation @ 54°C / 129°F (40/37/3)	ISO 6614 / ASTM D1401	minutes	10	10
Pour Point	ASTM D5950	°C (°F)	-15 (5)	-15 (5)
Flash Point - open cup method	ISO 2592 / ASTM D92	°C (°F)	>215 (>419)	>220 (>428)
Acid Number	ISO 6619 / ASTM D664	mgKOH/g	0.1	0.1
Rust test - synthetic seawater (24 hrs)	ISO 7120 / ASTM D665B	rating	Pass	Pass
Copper corrosion (3 hrs@100°C/ 212°F)	ISO 2160 / ASTM D130	rating	1b	1b
Oxidation Stability - Rotating Pressure Vessel test	ASTM D2272	minutes	1300	1300
Oxidation Stability - TOST	ISO 4263-1 / ASTM D943	hours	>10000	>10000
FZG Gear Scuffing test - A/8.3/90	ISO 14635-1 / ASTM D5182	Failure Load Stage	10	10

The above figures are typical of those obtained with normal production tolerance and do not constitute a specification.



Lube Control Pty Ltd

Storage

All packages should be stored under cover. Where outside storage is unavoidable drums should be laid horizontally to avoid the possible ingress of water and the obliteration of drum markings. Products should not be stored above 60°C, exposed to hot sun or freezing conditions.

Perfecto XEP Range
02 Dec 2025
Castrol, the Castrol logo and related marks are trademarks of Castrol Limited, used under licence.

This data sheet and the information it contains is believed to be accurate as of the date of printing. However, no warranty or representation, express or implied, is made as to its accuracy or completeness. Data provided is based on standard tests under laboratory conditions and is given as a guide only. Users are advised to ensure that they refer to the latest version of this data sheet. It is the responsibility of the user to evaluate and use products safely, to assess suitability for the intended application and to comply with all applicable laws and regulations. Safety Data Sheets are available for all our products and should be consulted for appropriate information regarding storage, safe handling, and disposal of the product. No responsibility is taken by either BP plc or its subsidiaries for any damage or injury resulting from abnormal use of the material, from any failure to adhere to recommendations, or from hazards inherent in the nature of the material. All products, services and information supplied are provided under our standard conditions of sale. You should consult our local representative if you require any further information.

The Technology Centre, Whitchurch Hill, Pangbourne, Reading, RG8 7QR, United Kingdom
+44 (0)203 915 7991