



Lube Control Pty Ltd



Product Data Sheet

Tribol™ GR 4020 PD Range

High performance bearing grease

Description

Castrol Tribol™ GR 4020 PD Range (previously called Tribol™ 4020 Range)greases are formulated from highly refined petroleum base oils, a lithium complex thickener, and Tribol Grease Oil Additive (TGOA), the latest advancement in the field of friction reducing and surface improving additive technology. These multi-service greases are designed to extend the service life of bearings in heavy duty and elevated temperature applications. The load-carrying, anti-wear, and friction reducing capabilities of Tribol GR 4020 PD greases exceed conventional complex greases due to the advanced TGOA additive technology. Under relatively high specific loads and related temperatures, this technology promotes a non-destructive smoothing of surface roughness in the micro-range.

This smoothing effect reduces friction and leads to an increase of the actual load-bearing surface. If surface roughness peaks redevelop because of shock loads or stop-and-go operation, the TGOA additive package automatically reactivates.

Surface roughness is again smoothed and lubrication optimised.

Application

Tribol GR 4020 PD greases were formulated as multi-service lubricants for heavy duty applications of plain and anti-friction bearings under medium to high loads. The TGOA additives are very effective in protecting the machined surfaces of bearings during the critical 'running-in' period. Good bearing surfaces are essential for long bearing life. Tribol GR 4020 PD is commonly used as a plant wide lubricant in the automotive industry as well as industries where the preference is for a high performance non-dark grease.

Advantages

- Advanced TGOA additive technology – multiple benefits including reduced friction, temperatures and noise, increased load carrying ability, and superior surface protection
- Excellent water resistance – the coating film stays on the surface even in the presence of water
- Excellent mechanical stability and adhesion – the grease keeps its consistency in service ensuring long term protection and reduced consumption as film stays between lubricated surfaces
- Superior oxidation resistance – prevents corrosive activity on bearings in aggressive environments
- Formulated to address environmental concerns – it is free of antimony, barium, lead, and zinc

Typical Characteristics

Name	Method	Units	GR 220-1 PD	GR 220-2 PD	GR 460-1 PD	GR 460-2 PD
Appearance	Visual	-	Light amber		Amber	
Thickener type	-	-	Lithium complex			
Base oil	-	-	Mineral oil			
Consistency	ASTM D217 / ISO 2137	NLGI Grade	1	2	1	2
Density @ 20°C	in house method	kg/m³	920	916	-	908
Worked Penetration (60 strokes @ 25°C)	ASTM D217 / ISO 2137	0.1 mm	310-340	265-295	310-340	265-295
Dropping Point	ASTM D566 / ISO 2176	°C	240	240	240	240
Base Oil Viscosity @ 40°C	ASTM D 445 / ISO 3104	mm²/s	220	220	460	460
Base Oil Viscosity @ 100°C	ASTM D 445 / ISO 3104	mm²/s	19	19	28.5	28.5
Flash Point - open cup method	ASTM D92 / ISO 2592	°C	225	225	232	232
Rust Test - distilled water (24hrs)	ASTM D665A / ISO 7120	Rating	Pass	Pass	Pass	Pass
Rust test - Emcor - distilled water	ASTM D6138 / ISO 11007	Rating	0/0	0/0	0/0	0/0
Copper Corrosion (24 hrs,100°C)	ASTM D130 / ISO 2160	Rating	1b	1b	1b	1b
Four Ball Wear test - Wear Scar Diameter (40 kgf / 75°C / 1200 rpm / 1 hr)	ASTM D2266 / ISO 51350	mm	0.5	0.5	0.5	0.5
Four Ball Weld Load test - Load Wear Index	ASTM D2783	kgf	80	80	80	80
Four Ball Weld Load test - Weld Point	ASTM D2783	kgf	400	400	400	400
Four Ball Wear test - Wear Scar Diameter	DIN 51350-5E	mm	0.7	0.7	0.7	0.7
Four Ball Wear test - Weld Load	DIN 51350-2	N	4200 / 4400	4200 / 4400	4200 / 4400	4200 / 4400
Timken OK Load	ASTM D2509	kg	23	23	23	23
SRV Friction and Wear test (300 N / 2 hr / 50°C)	ASTM D5707	coeff. of friction	0.08	0.08	0.08	0.08



Lube Control Pty Ltd

FE-9 Bearing Life test - A/1500/6000-140	DIN 51821-2	Pass	>100	>100	-	>100
Water Wash-out @ 79°C	ASTM D1264 / ISO 11009	%wt loss	4	4	4	4
Water Resistance	DIN 51807-1	Rating	1	1	1	1
Roll Stability test - Shear Stability	ASTM D1831	0.1 mm	10	10	10	10
Flow pressure @ -20°C	DIN 51805	mBar	500	850	1150	1300
DIN Classification	DIN 51502	-	KP 1 N-30	KP 2 N-30	-	KP 2 N-20
ISO Classification	ISO 6743/9	-	L- XBDHB-1	L- XBDHB-2	-	L- XBDHB-2

Subject to usual manufacturing tolerances.

Additional Information

In order to minimise potential incompatibilities when converting to a new grease, all previous lubricant should be removed as much as possible prior to operation. During initial operation, re-lubrication intervals should be monitored closely to ensure all previous lubricant is purged.
This product was previously called Tribol 4020 Range. The name was changed in 2015.

Tribol™ GR 4020 PD Range
18 Sep 2015
Castrol, the Castrol logo and related marks are trademarks of Castrol Limited, used under licence.

This data sheet and the information it contains is believed to be accurate as of the date of printing. However, to the extent that it is permissible by law to exclude warranties and representations, no warranty or representation, express or implied, is made as to its accuracy or completeness. Data provided is based on standard tests under laboratory conditions and is given as a guide only. Users are advised to ensure that they refer to the latest version of this data sheet. It is the responsibility of the user to evaluate and use products safely, to assess suitability for the intended application and to comply with all applicable laws and regulations. Material Safety Data Sheets are available for all our products and should be consulted for appropriate information regarding storage, safe handling, and disposal of the product. Refer to the MSDS, available from our website for further information. No responsibility is taken by either Castrol Australia , BP plc or its subsidiaries for any damage or injury resulting from abnormal use of the material, from any failure to adhere to recommendations, or from hazards inherent in the nature of the material. All products, services and information supplied are provided under our standard conditions of sale. You should consult our local representative if you require any further information.

Castrol Australia Pty Limited - ABN 87 008 459 407 – 717 Bourke Street, Docklands Vic 3008
Technical Advice Line: 1300 557 998 Customer Service: 1300 722 088